

KS Polyolefin-Adhesive-Set

Tips for use

1. The best results are obtained when the parts are bonded within one hour of application of the primer. A second application of K+S Polyolefin-Primer should not be applied within 8 hours of the original application.
2. As a result of its slightly basic properties, the primer also works as an activator and accelerates the hardening of K+S MULTI-PURPOSE ADHESIVE/MAGNUMBOND. After establishing the bond, functional firmness is usually reached within 30 seconds, however, a waiting time of 24 hours at 22°C should be observed so that the adhesive can develop its maximum firmness.
3. K+S Polyolefin-Primer fluoresce under UV light and thereby enables an application inspection with a UV lamp.
4. K+S Polyolefin-Primer is recommended for use in combination with K+S MULTI-PURPOSE ADHESIVE/MAGNUMBOND.
5. Do not use primer for materials that can be bonded with K+S MULTI-PURPOSE ADHESIVE/MAGNUMBOND alone.
6. Do not bring the nozzle of the adhesive bottle into contact with areas that were treated with primer.

