
AIR-board® UV PC

Our unique bonding technology enables us to combine a rigid translucent honeycomb core with transparent thermoplastic top sheets resulting in a panel with exceptional optical features.

The various types of panel in the AIR-board® family differ in their facing sheet materials, cores, surface structures, physical properties, dimensions and colours.



Product description

Facing sheet on both sides	Transparent polycarbonate
Core	PC-honeycomb (cell diameter 7mm)

Properties

- innovative translucent optics
- · unique 3D effects and light scattering
- excellent UV stability and resistance to weathering
- high light transmission with optimum privacy
- low weight
- easy processing
- compatibility with common mounting systems
- excellent rigidity
- high impact strength

Dimensions

Format	Length [mm]	Width [mm]	Thickness [mm]
Standard	3020	1220	19
Special dimensions*	max. 3500	max. 1500	max. 80

^{*} on request - minimum order per special size: 200m²

Tolerances	Length [mm]	Width [mm]	Thickness [mm]
Cut to size	+2/-2	+1/-2	+0/-1



General physical properties


Coefficient of thermal expansion acc. to DIN 53752-A	Service temperature	Fire class		G-Value (total energy transmission value)				
[1/K]	[°C]	DIN	BS 476	EN		Sola	r angle	
		4102-1	Part 7	13501	0°	30°	45°	60°
6.5 x 10 ⁻⁵	-30 bis +80	B1	1Y	B s2 d0	0.72	0.67	0.61	0,52

Thickness [mm]	Weight per unit area [kg/m²]	Thermal insulation U-value [W/m²K]	Sound insulation Rw [dB]	Bending stiffness* [Nm²]
12	5,4	3,2	21	196
16	5,6	2,7	21	444
19	5,9	2,4	21	532
30	6,6	1,7	23	1688
40	7,3	1,4	24	2987
60	8,7	1,1	25	3420
80	10,1	0,9	25	11093


^{*} per m panel width

Mounting systems for all AIR-board $^{ ext{ iny B}}$ panels


Profile system for dividing walls




Profile system for glazing



Tongue and groove joint



Furniture for hinged doors



All these specifications are based on our most up-to-date information but are subject to changes at any time.

A legally binding assurance of certain properties or the suitability of an individual type for a specific field of application cannot be assumed from these specifications.



