

# PMMA homopolymeric and copolymeric in sheet and block form

## Product data sheet

Chemical composition	96-100% depending on compound
PMMA (polymethyl acrylate)	
Functional monomers and other additives	0-4% depending on compound
Estimated molecular weight	between $3.8 \times 10^6$ and $9.5 \times 10^6$
Residual constituents of free monomers	<1% (typical 0.45%) depending on compound

CHARACTERISTICS	Value	Unit of measure	Standard
-----------------	-------	-----------------	----------

### MECHANICAL

Density	1.19	g/cm <sup>3</sup>	ISO 1183
Impact value	1.8	K/m <sup>2</sup>	ISO 180/1A
Tensile strength at 20°C	68	Mpa	ISO 527
Elongation at rupture	4	%	ISO 527
Bending properties	103	Mpa	ISO 178
Compressive strength	103	Mpa	ISO 604
Ball impact strength	166	Mpa	ISO 2039-1
Scratch resistance after grinding wheel test	37	%Haze	ISO 9532

### ACOUSTIC

Acoustic velocity at 20°C	2800	m/s
Estimated sound insulation value Rw for 10mm	32	dB

### OPTICAL

Transmittance	92.2	%	DIN 5036/3
UV-translucence	no		
Reflection loss	< 4	%	
Total energy transmission factor g	84	%	DIN EN 410
Absorption in visible range	< 0.05	%	
Optical refraction index	1.49		ISO 489

### ELECTRICAL

Earth resistance	> 10 <sup>14</sup>		DIN VDE 0303
Surface resistance	> 10 <sup>14</sup>		DIN VDE 0303
Dielectric coefficient at 60Hz	3.5		DIN VDE 0303
Dielectric loss factor at 60Hz	0.065		DIN VDE 0303

### BEHAVIOUR IN WATER

Water absorption 24h 20°C sample 65x65x2mm <sup>3</sup> Max. increase in weight	42	mg	ISO 62
after water absorption	2.2	%	ISO 62

### THERMAL

Linear coeff. of expansion between 0 and 55°C	0.07	mm/m°C	DIN 53572-A
Possible expansion through heat and moisture	7	mm/m	
Thermal conductivity	0.19	W/mK	DIN 52612
Coeff. of thermal conductivity sample 10mm	4.45	W/m <sup>2</sup> K	DIN 4701
Specific heat	1.47	J/gK	
Recommended forming temperature	140	C	
Maximum surface temperature	190	C	
Maximal recommended continued use temp.	81	C	
Relaxation temperature	> 85	C	
Auto-inflammation temperature	420	c	
Waste gas volume	low		
Toxicity of waste gases	no		
Corrosivity of waste gases	no		
Material class	B2		
Fire protection class	E		
Vicat-softening temperature	112	C	



### Contact us

Tel. (02) 9417 6111  
Fax. (02) 9417 6169

Web. [www.allplastics.com.au](http://www.allplastics.com.au)

Address. Unit 20/ 380 Eastern Valley Way, Chatswood, NSW 2067 AUSTRALIA.